Flammability Test Datasheet



Material Description

Lonseal PO#:

190061

Product Description: Loncoin II FW # 9822

Lot #:

LA-53/18

Item #:

C2F9822M72

Production #:

2158-040460

Backing:

Mesh

Date of Manufacture:

01/19

Thickness (mils):

92

Test Description and Results

14 CFR Part 25.853(a), Appendix F Part I(a)(1)(ii) Amendment 142, 12 second vertical bunsen burner.

Test Date: 1/30/2019 Witness: Keith Krueger Flame Temp (F): 1775

Trial	Burn Length (in):	Extinguishing Time (s)	Drip Time (s)
 1	1.2	5.9	No Drip
2	1	4.6	No Drip
3	1.3	2.7	No Drip
AVG	1.2	4.4	0

Comment:

Test Result: PASS

Testing was conducted to show that the subject material is compliant with the requirements of 14 CFR Part 25.853(a), Appendix F Part I(a)(1)(ii) Amendment 116, 12 second vertical bunsen burner. Test was conducted in accordance with Aircraft Materials Fire Test Handbook and Krueger Consulting Procedures Manual KF-1. All data is for quality control purposes only. Samples were not conformed and testing does not consitute FAA approval of the material.

Signed:

Keith Zwegen

1/30/2019

Keith Krueger

LONSEAL®
928 East 238th Street, Carson, CA 90745
p: 310-830-7111 | f: 310-830-9986 | e: info@lonseal.com

Certificate of Conformance

Lonseal Order #	0224981			
Customer PO #	IP-28732			
Lonseal Part #	C2F9822M72	Lonseal Lot #	LA-53/18	

Lonseal, Inc. certifies that the material supplied for the Purchase Order listed above conforms to Lonseal Corporation's material/process specification and are in all respects in conformance with the contract requirements. Lonseal, Inc. further certifies that the material meets 14 CFR $\S25.853(a)$ Appendix F Part I(a)(1)(ii), Amendment 116, 12 second vertical Bunsen burner, per the subsequent report.

Date:

7/21/2021

Signatures

Eric Neihouse

Manager of Technical Services and Quality Assurance

Revised: 1/15/2018