



TEST REPORT

DATE: 12/18/2007

TEST NUMBER: 111677


CLIENT	Lonseal, Inc.
TEST METHOD CONDUCTED	ASTM F925-02 24 Hour Standard Test Method for Resistance to Chemicals of Resilient Flooring
DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Loncoin I

TEST RESULTS

24 HOUR RATINGS

STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
Motor Oil	0	0	0
Transmission Oil	0	0	0
Bearing Grease	0	0	0
Brake Fluid	0	0	0
Radiator- Antifreeze	0	0	0
Brake Dust	0	0	0
Rubber (tires)	0	0	0
Differential/ Gear Box Oil	0	0	0
Premix Oil/ Gas Additive	0	0	0
Car Battery Acid (Leaky Battery)	0	0	0
Armor All Protectant	0	0	0
WD-40	0	0	0
Windshield Wiper Fluid	0	0	0

RATING KEY
0 - No change (----)
1 - Slight change
2 - Moderate change
3 - Severe change

APPROVED BY: 

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.