



# Fastbond™

## Pressure Sensitive Adhesives

### 4224-NF • Clear • Blue

Technical Data

July, 2005

**Description** 3M™ Fastbond™ Pressure Sensitive Adhesive 4224-NF is a water-based, permanently pressure sensitive adhesive with excellent initial tack and good bond strength.

- Features**
- Good UV and plasticizer resistance.
  - Excellent water resistance when dry.
  - Non-flammable in the wet state.
  - Adheres to most glass, paper, steel, galvanized steel, bare and clad aluminum, stainless steel, high impact styrene, PVC, ABS, polycarbonate and acrylic plastic surfaces.

**Typical Physical Properties**

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

<b>Viscosity (approx.):</b>	9,000 - 12,000 cps
<b>Brookfield Viscometer:</b>	RVF/RVT #6sp. @ 20 rpm @ 80°F
<b>Solids (by wt.):</b>	39-42%
<b>Base:</b>	Acrylate
<b>Color:</b>	Blue adhesive: wet – opaque blue dry – transparent blue  Clear adhesive: wet – white dry – clear
<b>Net weight (approx.):</b>	8.0 - 8.4 lbs./gal.
<b>Flash point:</b>	None
<b>Solvent:</b>	Water
<b>Coverage: (1 mil dry film) (approx.)</b>	670 sq. ft./gal.

**3M**  
**Fastbond™**  
**Pressure Sensitive Adhesives**  
 4224-NF • Clear • Blue

**Handling/Application Information**

**Directions for Use**

1. **Surface Preparation:** Surfaces must be clean, dry and dust free. Wiping with solvent such as 3M™ Scotch-Grip™ No. 3 or methyl ethyl ketone (MEK) will aid in removing oil and dirt.\* Plastic surfaces may be cleaned with isopropyl alcohol.\*
2. **Application Temperature:** For best results, the temperature of the adhesive and the surfaces being bonded should be at least 65°F (18°C).
3. **Application:** Spray, brush, roll or knife coat a smooth, uniform coat of adhesive to the least porous surface. Thickness of the adhesive will depend upon the surfaces being bonded and stress requirements and should be determined by the user. Porous or rough surfaces generally require more adhesive than smooth surfaces.
4. **Drying Time:** This will depend on the adhesive film thickness and drying temperature and should be determined by the user. Infrared heat may be used to speed up the drying process, if necessary. Generally, when the adhesive film has changed from an opaque, milky appearance to a clear or transparent and odorless state, drying can be considered complete. In order to maintain long term pressure sensitivity, the dry adhesive film must be kept free of dust or other contaminants through the use of a protective release liner.
5. **Bonding:** Bond surfaces together using firm pressure. A 3-inch wide (maximum) rubber roller (J-roller) is recommended. For maximum bond performance, the use of a nip-roll or rotary press is preferred. Bonding while one or both surfaces are warm will also help improve bond results.
6. **Cleanup:** Liquid adhesive can be removed from tools and equipment by flushing with large amounts of water. The addition of liquid soap and warm water will aid in cleanup. Dried adhesive may be removed with a solvent such as Scotch-Grip Solvent No. 3 or methyl ethyl ketone.\*

**\*Note:** When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

**Application Equipment Information**

**Note:** Appropriate application equipment can enhance adhesive performance. We suggest the following application equipment for the user's evaluation in light of the user's particular purpose and method of application.

1. **Pumping:** Use a 2:1 ratio divorced design stainless steel pump with Teflon® packings. Because these products contain water, pumping equipment should be stainless steel for maximum durability. Wetted parts of chrome or nickel should also be suitable.
2. **Spray:**

Spray Gun	Air Cap.	Fluid Tip	Air Pressure	Approx. Air Requirement	Fluid Flow
DeVilbiss JGV	30	E	10-15 PSI	5 CFM	12-24 fl. oz./min.
Binks 2001SS or No. 95	66 SD	66 SS	10-15 PSI	5 CFM	12-24 fl. oz./min.

**3M**  
**Fastbond™**  
**Pressure Sensitive Adhesives**  
 4224-NF • Clear • Blue

**Application/Equipment Information** (*continued*)

3. **Hoses:** All material hoses should be nylon lined. Do not use PVA hoses. Do not use fluid hoses previously used with solvent based adhesive since residual solvent will cause the water dispersion to coagulate. New fluid hoses should be installed when changing from a solvent to a water-based adhesive.
4. **Brushes and Rollers:** Brushes and rollers designed for latex paints are suggested.

**Typical Physical Properties**

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

Adhesive was tested in 180° (angle) peel, overlap shear, and dead load strength by first applying about a 6 mil (wet thickness) coating of adhesive to a primed polyester film. After drying, bonds were made to various substrates. Test results after 48 hrs. at 73°F (23°C) were as follows:

Substrate	Peel Strength (piw)	Overlap Shear (psi)
Glass	2.8	44
Cold Rolled Steel	4.4	48
Galvanized Steel	3.1	48
2024 T-3 Bare Aluminum	2.7	40
Clad Aluminum	2.3	45
Stainless Steel	4.2	48
High Density Polyethylene	1.5	33
Polypropylene	1.9	27
High Impact Polystyrene	2.9	47
PVC	3.4	46
ABS Plastic	3.6	44
Polycarbonate	3.3	50
Acrylic	3.0	44
Neoprene Rubber	1.6	13
EPDM Rubber	1.5	16

**Dead Load Shear:** The adhesive, knife coated on polyester film as above, was used to make 1 in. x 1/2 in. bonds to 2024-T3 bare aluminum. Various weights were then hung on the portion of the film extending below the bond area and the time required for the bond to fail was measured. The results were as follows:

Test Temperature	Time to Failure at a Load of:		
	2 psi	5 psi	10 psi
73°F (23°C)	24 + hrs.	24 + hrs.	6 hrs.
120°F (49°C)	24 + hrs.	2 hrs.	15 min.
160°F (71°C)	4 hrs.	11 min.	3 min.

# 3M

## Fastbond™

### Pressure Sensitive Adhesives

4224-NF • Clear • Blue

---

**Storage** Store product at 60-80°F (16-27°C) for maximum storage life. Freezing will cause irreversible coagulation of product. Keep containers tightly sealed when not in use.

---

**Shelf Life** When stored at the recommended conditions in the original, unopened containers, these products have a shelf life of 15 months.

---

**Precautionary Information** Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product.

---

**Product Use** All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

---

**Warranty and Limited Remedy** Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

---

**Limitation of Liability** Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**ISO 9001:2000**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



#### Industrial Business Industrial Adhesives and Tapes Division

3M Center, Building 21-1W-10, 900 Bush Avenue  
St. Paul, MN 55144-1000  
800-362-3550 • 877-369-2923 (fax)  
www.3M.com/industrial



Recycled Paper  
40% pre-consumer  
10% post-consumer

Teflon is a registered trademark  
of E.I. DuPont de Nemours Co.  
Printed in U.S.A.

©3M 2005 78-6900-9943-3 (7/05)